





SAFPLANK HD®

HEAVY DUTY DECKING SYSTEM





Features

SAFPLANK HD® is a high strength system of fiberglass planks designed to form a continuous solid surface. SAFPLANK HD® is intended to replace wood, aluminum or steel planks in environments where corrosion or rotting creates costly maintenance problems or unsafe conditions.

SAFPLANK HD® panels are:

- Corrosion Resistant
- Strong
- Easy to Maintain
- Non-sparking
- Easy to Install
- Lightweight
- Low Conductivity

Sizes

SAFPLANK HD® is available in 6" (152.4 mm) deep panels in 36" (914.4 mm) width. Stock panels are available in 24' (7.32 m) lengths. Other lengths are available upon request. SAFPLANK HD® may be ordered with a grit surface or with a smooth surface for non-pedestrian applications.

Materials of Construction

SAFPLANK HD® is a composite of fiberglass reinforcements (glass roving and continuous filament mat) and a thermoset resin system. The pultrusion

process is used to produce the panels. Planks can be manufactured using polyester resin to ANSI/NSF standard 61 certified for potable water applications, if required.

The standard resin system is a slate gray fire retardant polyester resin meeting the requirements of Class 1 flame spread rating of 25 or less per ASTM E-84 and the self-extinguishing requirements of ASTM D-635. The resin is UV inhibited and the composite incorporates a surface veil on all exposed surfaces for enhanced corrosion and UV protection. Other resins and colors are available upon request.

The standard grit system for SAFPLANK HD® is a polyurethane based medium grit. This grit system is recommended for light pedestrian traffic only. Other grit systems available include epoxy medium and epoxy coarse and may be more appropriate for applications with heavier traffic.

Applications

SAFPLANK HD® is designed to be used for numerous applications including:


- Temporary Flooring
- Windwalls
- Roofing Walkways
- Concrete Forming Systems
- Odor Control Covers
- Dock Surfacing
- Cellular Wall Panels

SAFPLANK HD[®] MECHANICAL PROPERTIES

Uniform Load

LOAD in LB / SQUARE FOOT (PSF) or KG / SQUARE METER (KG/M²)

I = 129.8 in.⁴, A = 25.0 in.², wt = 21.0 lb / lin. ft. or I = 5.4 x 10⁷ mm⁴, A = 16,129 mm², wt = 31.32 kg / lin. m




SPAN	40 (195.30)		60 (292.95)		80 (390.60)		100 (488.24)	
	Deflection	L/Ratio	Deflection	L/Ratio	Deflection	L/Ratio	Deflection	L/Ratio
10 ft 3.05 m	0.07 in 1.78 mm	1731	0.10 in 2.54 mm	1154	0.14 in 3.56 mm	865	0.17 in 4.32 mm	692
12 ft 3.66 m	0.14 in 3.56 mm	1002	0.22 in 5.59 mm	668	0.29 in 7.37 mm	501	0.36 in 9.14 mm	401
14 ft 4.27 m	0.27 in 6.86 mm	631	0.40 in 10.16 mm	420	0.53 in 13.46 mm	315	0.67 in 17.02 mm	252
16 ft 4.88 m	0.45 in 11.43 mm	423	0.68 in 17.27 mm	282	0.91 in 23.11 mm	211	1.14 in 28.96 mm	169
18 ft 5.49 m	0.73 in 18.54 mm	297	1.09 in 27.69 mm	198	1.46 in 37.08 mm	148		
20 ft 6.10 m	1.11 in 28.19 mm	216						
22 ft 6.71 m	1.62 in 41.15 mm	163						

Concentrated Line Load

LOAD in LB / FOOT of WIDTH or KG / METER of WIDTH

I = 129.8 in.⁴, A = 25.0 in.², wt = 21.0 lb / lin. ft. or I = 5.4 x 10⁷ mm⁴, A = 16,129 mm², wt = 31.32 kg / lin. m



SPAN	100 (148.82)		300 (446.45)		600 (892.90)	
	Deflection	L/Ratio	Deflection	L/Ratio	Deflection	L/Ratio
10 ft 3.05 m	0.03 in 0.76 mm	4327	0.08 in 2.03 mm	1442	0.17 in 4.32 mm	721
12 ft 3.66 m	0.05 in 1.27 mm	3005	0.14 in 3.56 mm	1002	0.29 in 7.37 mm	501
14 ft 4.27 m	0.08 in 2.03 mm	2207	0.23 in 5.84 mm	736	0.46 in 11.68 mm	368
16 ft 4.88 m	0.11 in 2.79 mm	1690	0.34 in 8.64 mm	563	0.68 in 17.27 mm	282
18 ft 5.49 m	0.16 in 4.06 mm	1335	0.49 in 12.44 mm	445	0.97 in 24.64 mm	223
20 ft 6.10 m	0.22 in 5.59 mm	1082	0.67 in 17.02 mm	361	1.33 in 33.78 mm	180
22 ft 6.71 m	0.30 in 7.62 mm	894	0.89 in 22.61 mm	298		

Notes:

Contact Strongwell for higher load conditions than what is tabulated.

Values are limited to deflection ratios less than L/150 or a maximum span of 22 feet (6.71 meters).

Material Property Data:

Full Section Modulus of Elasticity = 3,000,000 psi (minimum) or 20.6 x 10³ N/mm²


Coefficient of Thermal Expansion (LW) = 4.7 x 10⁻⁶ in./in./°F or 8.5 x 10⁻⁶ mm/mm/°C

Coefficient of Thermal Expansion (CW) = 13.9 x 10⁻⁶ in./in./°F or 2.4 x 10⁻⁵ mm/mm/°C


EXTREN[®] Minimum Material Strength Properties for Lengthwise and Crosswise Directions

CONNECTION OPTIONS

Anchor & Angle




Anchor Bolt Only




END CLOSURE OPTIONS

Flush



Step



STRONGWELL

ISO-9001 Quality Certified Manufacturing Plants

BRISTOL LOCATION

400 Commonwealth Ave., P. O. Box 580, Bristol, VA 24203-0580 USA
(276) 645-8000

www.strongwell.com